



FURBISH CHEMICAL & SUPPLY CO. Of ALASKA, INC.

501 Raspberry Road

Anchorage, Alaska 99518-1569

Phone (907) 344-4184 Fax (907) 344-5919

FOREVER FLOOR FINISH

FLOOR FINISH OF THE FUTURE
FOR THE FLOOR OF TODAY

DESCRIPTION: This floor finish is an innovative blend of thermal plastic acrylic resins, polyurethane and multi-poly waxes. This balance of ingredients makes this a futuristic product in high speed finishes. This new formula changes the age old question of *quantity* of solids to a new question of *quality* of solids. This unique product's solid content is 26% polyurethane. This increased reinforcement improves the durability and strength of floor finish.

ADVANTAGES:

- Urethane fortified to improve wearability.
- Outstanding slip resistance.
- Higher initial gloss with fewer coats.
- Easy to apply.
- Excellent re-coating properties.
- Minimum loss of gloss due to traffic scuffing.
- High speeds to a set gloss look.
- Extremely black mark resistant.
- Resistant against strong alkaline cleaner.
- Exceptional resistance to powdering.

RECOMMENDED USE: This floor finish is formulated to increase and protect the life of asphalt, vinyl asbestos, vinyl, and linoleum resilient flooring. Excellent for use on ceramic tile, marble, terrazzo and sealed wood floors. It adheres well to painted floors. Extremely porous floors may require a sealer first.

DIRECTIONS: Strip floors with either a conventional stripper or a mop and strip product. When you use a conventional stripper, always rinse and neutralize your floors for optimum results. With a mop and strip non rinse product always tack mop to remove any leftover residue.

SEALER: "Optional" - apply two coats of sealer. First coat medium to heavy and second coat thin to medium. Let dry well between coats.

FINISH: Sealed Floor - Always put at least two coats of finish over sealer. Unsealed Floor - Apply at least three coats of finish allowing sufficient time to dry between coats. Drying time usually is from 15 minutes to 30 minutes depending on conditions.

FOLLOW UP MAINTENANCE: High speed entire floor on first time follow-up using a high quality spray buff maintainer or a mop-on type material. After initial high speeding, high speed traffic areas where scuffs or marks are present on a scheduled basis or on an as needed basis: When wear begins to show, clean floor thoroughly and rinse well. Apply one to two coats of floor finish. Always use good maintenance procedures in dust-mopping and/or damp-mopping according to your needs.

NOTICE:

The information contained herein, is to the best of our knowledge and belief, accurate. Since the conditions of handling and use are beyond our control, we make no guarantee of results. We assume no liability for damages or penalties resulting from our suggestions or recommendations, nor are these to be taken as a license to operate under, or recommendations to infringe, any patent.

SPECIFICATIONS:

Detergent resistance	Excellent
Color	White emulsion
Film Color	Clear
Odor	Mild polymer odor
pH	8.0 ± 8.5
Drying time	Average 20 minutes
Recoatibility	Excellent
Leveling	Excellent
Stability	Minimum 2 years
Water resistance	Excellent
Initial Gloss	100/100 (60E specular gloss)
Weight Per Gallon	8.55 lbs/gal
Slip Resistance (James Machine)	>6
Slip Resistance (Foot Pressure)	Excellent
Scuff Resistance	Outstanding
Gloss Retention	Excellent
Heel Mark Resistance	Excellent
Film Powdering	None
Coverage	>2000 sq ft/gal
Refractive Index	26 ± 1
Specific Gravity	1.027 ± .005

CAUTION
KEEP OUT OF REACH OF CHILDREN
DO NOT TAKE INTERNALLY
PROTECT FROM FREEZING